

## *Specifications Of Cylinder Oil No. (12) Importation*

TEST	METHOD	SPECIFICATION
<b>Kin. Viscosity @ 40 °C</b> <b>cSt</b>	ASTM - 445	-
<b>Kin. Viscosity @ 100 °C</b> <b>cSt</b>	ASTM - 445	44
<b>Viscosity Index</b>	ASTM - 2270	Min. 78
<b>Flash Point by P.M Closed °C</b> <b>( Min )</b>	ASTM - 93	250
<b>Pour Point</b>	ASTM - 97	Max +2
<b>Conradson Carbon Residue</b> <b>% mass</b> <b>( Max )</b>	ASTM - 189	3.3
<b>Total Acidity</b> <b>mgKOH / g</b> <b>( Max )</b>	ASTM - 974	0.3
<b>Ash Content</b> <b>% mass</b> <b>( Max )</b>	ASTM - 482	0.01
<b>Appearance</b>	By Vision	Olive Green